
LOW-DENSITY CLOSED-CELL PVC FOAM TAPE



CATEGORY













STRUCTURAL SPACER

COMPRESSIBLE GLAZING

WEATHERSTRIPPING

RESIDENTIAL GLAZING

ULTRA HIGH-BOND

PE MOUNTING

INDUSTRY

AUTOMOTIVE

RECREATIONAL VEHICLES GLAZING

CONSTRUCTION DETAILING

GASKETING

ACOUSTICS

LOG HOME

MOUNTING

PROTECTIVE

TAPE OVERVIEW

The V810 Low-Density & Weatherstripping Tape from Capital Tape is an automotivegrade tape used when air- and moisturetight seals on irregular surfaces are critical. Easy to compress, nearly impossible to destroy.

- Easy to compress and conformable
- Strong and resilient
- Ultra flexible to seal tight radius or irregular surfaces
- Excellent resistance to fungi, oxidation, and weather
- Fire rating: Meets/exceeds FMVSS 302A
- Self-Extinguishing



SCAN FOR MORE

Visit this product page, request samples, or get an online quote.

TAPE PROPERTIES

The values stated in charts are averages and are not to be construed as a warranty. Products must be tested by end user for application suitability.

| Density | ASTM D-1667 | 8 lbs./cu. ft. |
|--|---------------------------------|----------------|
| Hardness (Shore 00) | ASTM D-2240 | 25 |
| Force to Compress (@ 25%) | ASTM D-1667 | 2 PSI/14 kPa |
| Compression Set (@ 25%) | ASTM D-1667 | 4% |
| Tensile Strength | ASTM D-412 | 30 PSI/207 kPA |
| Peel Adhesion | ASTM D-1000 | 2 lbs |
| Water absorption (% by volume) | GTP | 1.0 |
| Percent Elongation | ASTM D-412 | 150 |
| Thermal Conductivity | ASTM C-518 | 0.27 |
| Recommended Service Temp. 12 month shelf life | -40°F to 180°F -40°C to 80°C | |
| Recommended Application Temperature | 50°F to 110°F 10°C to 45°C | |
| Fungi resistance | Excellent | |
| Oxidation resistance | Excellent | |
| Weather resistance | Excellent | |









