CT4725BK

CLOSED-CELL ACRYLIC FOAM TAPE

CapitalTape
A family business, since 1990

CATEGORY


STRUCTURAL SPACER


COMPRESSIBLE GLAZING


WEATHERSTRIPPING


RESIDENTIAL GLAZING


ULTRA HIGH-BOND

PE MOUNTING

INDUSTRY **AUTOMOTIVE** **RECREATIONAL VEHICLES** **GLAZING** **CONSTRUCTION DETAILING** GASKETING ACOUSTICS LOG HOME **MOUNTING** PROTECTIVE

TAPE OVERVIEW

The CT4725BK is an acrylic foam with high tack and shear strength; excellent resistance to solvents, chemicals, UV and heat; clear with a red plastic release liner. This product has a very high initial tack and can be used on most surfaces.

- **High tack and shear strength**
- **Ideal for use on most surfaces**
- **Excellent UV resistance**
- **Excellent resistance to extreme heat**
- **Excellent resistance to solvents**
- **Excellent resistance to chemicals**

SCAN FOR MORE

Visit this product page, request samples, or get an online quote.

TAPE PROPERTIES

The values stated in charts are averages and are not to be construed as a warranty. Products must be tested by end user for application suitability.

Thickness		.025" / 25 mil
Length		108 ft / 36 yds
Density		37 lbs. / ft^3 600 kg / m^3
Temperature Resistance		Minimum -40˚F / -40˚C Short term 248˚F / 120˚C Long term 194˚F / 90˚C
90˚ Peel Adhesion*	ASTM D-3330	26 N/10mm (15 lbs/in)
Dynamic Shear*	ASTM D-1002	760 kPa (110 lbs/in^2)
Tensile Strength	ASTM D-897	730 kPa (106 lbs/in^2)
Static Shear **> 10,000 minutes (7 days)**	ASTM D-3654	22˚C (72˚F) – 1000 g/312mm^2 66˚C (150˚F) – 500 g/312mm^2 93˚C (200˚F) – 500 g/312mm^2

*Adhesion and Static Shear testing done on stainless steel

MEMBER NGA NATIONAL GLASS ASSOCIATION

FMVSS 302A
Federal Motor Vehicle Safety Standard No. 302
CAPITAL TAPE

A.A.M.A. CERTIFIED 810.1-16 Type I

WE CUT TAPE. Learn more at capitaltape.com

1-888-888-TAPE service@capitaltape.com 4920 Commerce Parkway #11, Cleveland, OH 44128